

IN-PAKT PRECISION CT GROUT

Pre-packaged, high performance, pumpable, non-shrink, cementitious grout for cold temperature applications.

In-Pakt Precision CT Grout is a cement based, nonmetallic, non-shrink grout containing well graded, natural, fine aggregate, silica fume and other carefully selected components. In-Pakt Precision CT Grout meets ASTM C 1107, type C grout and can be used at varying consistencies from dry pack to fluid in temperatures above -5°C (23°F).

FEATURES & BENEFITS

- Can be mixed and placed from dry pack, plastic and fluid consistencies using relatively low water/cement ratios.
- Excellent pumpability.
- Improved resistance to washout.
- Achieves hardened properties in cold temperature conditions.
- Very low permeability.
- Non-corrosive, non-chloride, non-metallic.
- Excellent resistance to freeze-thaw cycling and salt-scaling in the presence of de-icing salts.
- All King products are manufactured using ISO 9001:2000 Certified Processes.

USES

- Grouting machinery base plates and column sole plates.
- Grouting anchor bolts, dowels and hand rails.
- Repair of precast units.
- Infill of pipes and sleeves in marine environments.
- Contact KING Technical Support Staff for recommendations or information on uses or conditions not listed.

PROCEDURES

Surface Preparation:

All surfaces to be in contact with In-Pakt Precision CT Grout must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all delaminated or unsound concrete providing a roughened surface. To avoid freezing of the interface between the grout and the parent concrete, do not pre-wet the receiving surface. Pneumatically remove any free standing or other fine particles that may interfere with the bond between the In-Pakt Precision CT Grout and the substrate.

When temperatures are below freezing for 24 hours but not lower than -5°C (23°F), the temperature of the substrate, plates and grout must be warmed at 5°C (40°F) prior to placement. The temperature of the grouted area must be maintained above 0°C (32°F) for 24 hours after application.

When temperatures are below -5°C (23°F), the temperature of the substrate, plates and grout must be warmed at 5°C (40°F) for 24 hours prior to placement. The temperature of the grouted area must be maintained above 0°C (32°F) for 24 hours after application.

Water Proportioning For Grout Consistency:

The following amounts of water will produce the following grout consistencies:

Dry Pack – approx. 2.35 litres (0.62 US gallon) of water

Plastic – approx. 3.0 litres (0.79 US gallon) of water

Fluid – approx. 4.4 litres (1.16 US gallon) of water

Note: Water requirement varies with temperature. Increase water slightly as temperature rises and decrease water slightly as temperature decreases.

Mixing:

Place 75 % of required water into mixer and slowly introduce entire bag of In-Pakt Precision CT Grout. Add balance of required water slowly while mixer is running, not exceeding maximum recommended volume of water. Continue mixing for a minimum of 3 minutes and stop only when material has obtained a consistent homogeneous mix. Allow 5 minutes mixing time if using a spiral blade drill mixer. Keep grout mix well agitated until placed.

Placing:

Dry Pack – Firmly press or ram In-Pakt Precision CT Grout into place using metal or hardwood tamping tools and a mason's trowel. Grout consistency when pressed into a firm ball should display no cracking or excessive surface moisture.

Plastic – Rod In-Pakt Precision CT Grout into place or trowel into areas where material can not flow into place. Grout consistency should be similar to that of a masonry mortar (between 100 – 115 % flow, ASTM C 1437).

Fluid – In-Pakt Precision CT Grout may be poured or pumped into place. Pour continuously with adequate head pressure or pump into place ensuring that all voids are completely filled. Formwork joints should be caulked with suitable material. Adequately vent high points to allow entrapped air to escape.

Curing:

A resin based liquid membrane curing compound approved for use in cold weather conditions that complies with ASTM C 309 should be applied immediately after grout reaches final set.

TECHNICAL DATA

The following data is representative of typical values achievable under laboratory conditions. Results in the field may vary.

	DRY PACK	PLASTIC	FLUID
MIXING RATIO PER 25 KG (55 LB.)			
	2.35 litres (0.62 US gallon)	3.0 litres (0.79 US gallon)	4.4 litres (1.16 US gallon)
WORKING TIME	30 minutes	60 minutes	60 minutes
FLOW TABLE ASTM C 1437		110 %*	> 150 %
FLOW CONE ASTM C 939			30 seconds

IN-PAKT PRECISION CT GROUT

	DRY PACK	PLASTIC	FLUID
WET DENSITY ASTM C 138		2127 kg/m ³ (132 lb./ft ³)	2170 kg/m ³ (135 lb./ft ³)
SET TIME ASTM C 191 METHOD A			
Initial Set		3.0 hours	5.5 hours
Final Set		3.5 hours	7.0 hours
COMPRESSIVE STRENGTH ASTM C 109			
1 Day		25 MPa (3625 psi)	15 MPa (2175 psi)
3 Day	40 MPa (5800 psi)	30 MPa (4350 psi)	20 MPa (2900 psi)
7 Day	45 MPa (6525 psi)	45 MPa (6525 psi)	35 MPa (5070 psi)
28 Day	55 MPa (7975 psi)	55 MPa (7975 psi)	40 MPa (5800 psi)
COMPRESSIVE STRENGTH ASTM C 109 (AT 5°C (40°F))*			
1 Day		5 MPa (725 psi)	
3 Day		25 MPa (3625 psi)	
7 Day		30 MPa (4350 psi)	
28 Day		40 MPa (5800 psi)	
SPLITTING TENSILE STRENGTH ASTM C 496			
28 Day		4.0 MPa (580 psi)	3.5 MPa (505 psi)
BOND STRENGTH BY SLANT SHEAR ASTM C 882			
28 Day		35 MPa (5075 psi)	35 MPa (5075 psi)
MODULUS OF ELASTICITY ASTM C 469			
28 Day		26.0 GPa (3.8 x 10 ⁶ psi)	19.5 GPa (2.8 x 10 ⁶ psi)
HARDENED HEIGHT CHANGE ASTM C 1090			
28 Day		0.10 %	0.35 %

	DRY PACK	PLASTIC	FLUID
WATER ABSORPTION ASTM C 642		8.2 %	13.0 %
FREEZE-THAW RESISTANCE ASTM C 666		100 % (Excellent durability factor)	107 %
DE-ICING SALT SCALING RESISTANCE ASTM C 672			
25 Cycles		0.02 kg/m ² (0.004 lb./ft ²)	0.04 kg/m ² (0.008 lb./ft ²)
50 Cycles		0.22 kg/m ² (0.05 lb./ft ²)	0.20 kg/m ² (0.04 lb./ft ²)

* Laboratory conditions with material and ambient temperatures kept at 5°C (40°F).

OPTIMUM PERFORMANCE

- Not recommended for areas of extremely high vibration.
- For void filling applications larger than 50 mm (2 in.), use MS Self-Consolidating Concrete.

YIELD

	PLASTIC	FLUID
25 kg (55 lb.)	0.013 m ³ 0.47 ft ³	0.014 m ³ 0.49 ft ³

PACKAGING

In-Pakt Precision CT Grout is normally packaged in 25 kg (55 lb.) triple lined bags and poly wrapped on wooden pallets. All KING can be custom packaged to suit specific job requirements.

STORAGE AND SHELF LIFE

Material should be stored in a dry covered area protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

In-Pakt Precision CT Grout contains Portland cement. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Material Safety Data Sheets are available upon request.

.....
This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade.

V0708

KING PACKAGED MATERIALS COMPANY

Burlington Office
3385 Harvester Rd.
Burlington, ON
L7N 3N2
Phone: (905) 639-2993
Fax: (905) 333-3730

Blainville Office
650 Boul. Labelle
Blainville, QC
J7C 2J2
Phone: (450) 430-4104
Fax: (450) 430-6855

Brantford Office
541 Oak Park Rd.
Brantford, ON
N3T 5L8
Phone: (519) 756-6177
Fax: (519) 756-7490

Sudbury Office
644 Simmons Rd.
Dowling, ON
POM 1R0
Phone: (705) 855-1155
Fax: (705) 855-1122