

MS-S6 CONCRETE

High performance, multi purpose, pre-packaged concrete repair material.

MS-S6 Concrete is a pre-blended, synthetic fiber reinforced, pre-packaged high performance cementitious concrete repair material containing Portland cement, silica fume, air-entraining admixture, 6 mm (¼ inch) stone and other carefully selected components.

FEATURES & BENEFITS

- Air-entrainment provides superior resistance to freeze-thaw cycling and salt scaling resistance.
- Properties similar to conventional concrete, thus offering excellent compatibility to parent concrete.
- Good workability.
- Improved durability.
- Reduced bleeding.
- Improved resistance to sulphate attack.
- Very low permeability.
- Low shrinkage.
- All King products are manufactured using ISO 9001:2000 Certified Processes.

USES

- Partial and full depth rehabilitation of concrete beams, columns, and/or soffits in bridges, parking garages, balconies or other concrete structures.
- New concrete construction, especially areas subject to freeze-thaw cycles and high salt (chloride) environments.

PROCEDURES

Surface Preparation:

All surfaces to be in contact with MS-S6 Concrete must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all delaminated or unsound concrete providing a roughened surface and a minimum of 25 mm (1 inch) clearance behind any corroded reinforcing steel. The perimeter of the repair area should be sawcut a minimum of 20 mm (¾ inch). Clean the area to be repaired with potable water, leaving the concrete saturated but free of standing water (SSD).

Mixing:

Place 75 % of required water into mixer and slowly introduce entire bag of MS-S6 Concrete. Add balance of required water slowly while mixer is running, not exceeding maximum recommended volume of water. **Maximum recommended volume of water is 2.6 litres (0.7 US gallons) per 30 kg (66 lb.) bag.** Continue mixing for a minimum of 3 minutes and stop only when material has obtained a consistent homogeneous mix.

Placing:

Mix and substrate temperatures should be maintained between 5 to 30°C (40 to 86°F).

In cold weather, hot water may be used to increase mix temperature and avoid lengthy set times. Do not place MS-S6 Concrete when ambient temperature is below 5°C (40°F). Refer to ACI 306, "Cold Weather Concreting".

In warm weather, ice water may be used as mix water to cool mix temperature and avoid short working time. Evaporation retarder should be considered to improve finishability. When ambient temperature is above 30°C (86°F), refer to ACI 305, "Hot Weather Concreting".

Place material uniformly and consolidate by forcing it down to the surface of the parent concrete and around the underside of the rebar using a trowel, a wood float or by rodding the material. Ensure material has completely encapsulated any exposed rebar. For slab finishing, the use of a wood float is recommended.

Curing:

Curing is essential to optimize physical properties of the concrete and minimize plastic shrinkage. MS-S6 Concrete should be cured immediately after material has reached initial set in accordance with ACI 308 "Guide to Curing Concrete". Continuously moist cure for a minimum period of 7 days. Alternatively, moist cure for a minimum period of 24 hours and apply King Duro-Cure curing compound or a curing compound that complies with ASTM C 309. Curing is particularly critical in rapid moisture loss conditions such as high temperatures, high winds and low humidity.

TECHNICAL DATA

The following data is representative of typical values achievable under laboratory conditions. Results in the field may vary.

MASS DENSITY

ASTM C 39 2310 kg/m³ (144 lb./ft³)

COMPRESSIVE STRENGTH

ASTM C 39

1 Day 20 MPa (2900 psi)
 3 Day 25 MPa (3625 psi)
 7 Day 35 MPa (5075 psi)
 28 Day 45 MPa (6500 psi)

FLEXURAL STRENGTH

ASTM C 78

7 Day 7 MPa (1000 psi)
 28 Day 12 MPa (1740 psi)

BOND STRENGTH BY SLANT SHEAR

ASTM C 882

7 Day 7.4 MPa (1070 psi)
 28 Day 19.4 MPa (2810 psi)

UNIAXIAL DRYING SHRINKAGE

ASTM C 157

28 Day 670 µm/m
 60 Day 850 µm/m

SALT SCALING RESISTANCE

ASTM C 672

50 cycles < 0.1 kg/m² (0.02 lb./ft²)

FREEZE-THAW RESISTANCE

ASTM C 666

98 %
 (Excellent durability factor)

RAPID CHLORIDE PERMEABILITY

ASTM C 1202

350 Coulombs

MS-S6 CONCRETE**OPTIMUM PERFORMANCE**

- Place MS-S6 Concrete at a minimum thickness of 25 mm (1 inch).
- For full depth repair or for repair edges longer than 1 m (3 ft), refer to MS-S10 Concrete.

YIELD

30 kg (66 lb.) bag contains approximately 0.014 m³ (0.5 ft³).

PACKAGING

MS-S6 Concrete is normally packaged in 30 kg (66 lb.) triple lined bags and poly wrapped on wooden pallets. All KING products can be custom packaged to suit specific job requirements.

STORAGE AND SHELF LIFE

Material should be stored in a dry covered area protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

MS-S6 Concrete contains Portland cement. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Material Safety Data Sheets are available upon request.

.....
This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade.

V0709

KING PACKAGED MATERIALS COMPANY

Burlington Office
3385 Harvester Rd.
Burlington, ON
L7N 3N2
Phone: (905) 639-2993
Fax: (905) 333-3730

Blainville Office
650 Boul. Labelle
Blainville, QC
J7C 2J2
Phone: (450) 430-4104
Fax: (450) 430-6855

Brantford Office
541 Oak Park Rd.
Brantford, ON
N3T 5L8
Phone: (519) 756-6177
Fax: (519) 756-7490

Sudbury Office
644 Simmons Rd.
Dowling, ON
P0M 1R0
Phone: (705) 855-1155
Fax: (705) 855-1122