

PC-35 MINING CONCRETE

Pre-packaged 35 MPa concrete mix for underground construction.

PC-35 Mining Concrete is a pre-blended, pre-packaged, 35 MPa concrete mix containing Portland cement, fine and coarse aggregate and other carefully selected components.

FEATURES & BENEFITS

- Requires only the addition of water.
- Excellent pumpability.
- All King products are manufactured using ISO 9001:2000 Certified Processes.

USES

- Construction of concrete floor slabs, walls, grizzlies, door frames and other underground concrete structures.

PROCEDURES

Mixing:

Mix material at a maximum water-cement ratio of 0.5 (~100 L per 1,000 kg bag or ~26.5 US gallons per 2,205 lb. bag). Maximum slump should be 100 mm (4 inches). For mixing instructions, follow recommendations of concrete mixer manufacturer.

Placing:

Place material uniformly and consolidate by vibrating. Ensure material has completely encapsulated any rebar or welded wire mesh. Refer to ACI 304R – “Guide for Measuring, Mixing, Transporting and Placing Concrete”. Any formwork should be rigid and tight to prevent loss of material. For forming applications, refer to ACI 347, “Recommended Practice for Concrete Formwork”.

Curing:

Good curing conditions are beneficial to optimizing physical properties of PC-35 Mining Concrete. Although the high relative humidity commonly found in underground environments provides for good curing conditions, additional curing is often appropriate and should be performed in accordance with ACI 308 “Standard Practice for Curing Concrete”.

TECHNICAL DATA

The following data is representative of typical values achievable under laboratory conditions. Results in the field may vary.

MASS DENSITY

ASTM C 39 2375 kg/m³ (148 lb./ft³)

COMPRESSIVE STRENGTH

ASTM C 39

3 Day 20 MPa (2900 psi)

7 Day 25 MPa (3620 psi)

28 Day 35 MPa (5070 psi)

FLEXURAL STRENGTH

ASTM C 78

28 Day 6 MPa (2030 psi)

OPTIMUM PERFORMANCE

- PC-35 Mining Concrete can be mixed using Minequip CCM 200 Continuous Mixer (contact a KING representative for details).
- PC-35 Mining Concrete can also be poured using a dry-mix shotcrete machine and a Minequip Separator Box (contact a KING representative for details).

YIELD

- 30 kg (66 lb.) bag contains approximately 0.014 m³ (0.5 ft³).
- 1,000 kg (2,205 lb.) bag contains approximately 0.45 m³ (16.5 ft³).

PACKAGING

PC-35 Mining Concrete is normally packaged in 1,000 kg (2,205 lb.) re-useable bulk bags and poly wrapped on wooden pallets. Material can also be supplied in 30 kg (66 lb.) triple lined bags or through bulk delivery. All KING products can be custom packaged to suit specific job requirements.

STORAGE AND SHELF LIFE

Material should be stored in a dry covered area protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

PC-35 Mining Concrete contains Portland cement. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Material Safety Data Sheets are available upon request.

.....
This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade.

V0708



Mixing Strength With Satisfaction

DIVISION 03300

PC-35 MINING CONCRETE

KING PACKAGED MATERIALS COMPANY

Burlington Office
3385 Harvester Rd.
Burlington, ON
L7N 3N2
Phone: (905) 639-2993
Fax: (905) 333-3730

Blainville Office
650 Boul. Labelle
Blainville, QC
J7C 2J2
Phone: (450) 430-4104
Fax: (450) 430-6855

Brantford Office
541 Oak Park Rd.
Brantford, ON
N3T 5L8
Phone: (519) 756-6177
Fax: (519) 756-7490

Sudbury Office
644 Simmons Rd.
Dowling, ON
P0M 1R0
Phone: (705) 855-1155
Fax: (705) 855-1122